

Application No.: 09/974040Case No.: 56685US002**Amendments to the Claims:**

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Please cancel claims 5, 6, 25-28, 30 and 31

**Listing of Claims**

1. (previously presented) A co-extruded, uni-axially oriented multi-layer film comprising a co-extruded uni-axially oriented microfiber layer, wherein the film comprises two opposing surfaces, each surface comprising microfibers, and wherein one surface is hydrophilic and one surface is hydrophobic.
2. (original) The film of claim 1 wherein the film is uni-axially oriented by stretching in one direction relatively more than stretching in a perpendicular direction.
3. (canceled)
4. (canceled)
5. (canceled)
6. (canceled)
7. (original) The film of claim 1 comprising a microfiber layer and a non-microfiber layer, the microfiber layer comprising a material that exhibits a property selected from the group consisting of hydrophobicity, hydrophilicity, oleophobicity, oleophilicity, a dielectric property, low coefficient of friction, stain resistance, flame retardance, high strength or modulus, an ability to produce a certain size microfiber, and combinations thereof, and the non-microfiber layer comprising a material selected from the group consisting of a hydrophobic material, a hydrophilic material, an elastomeric material, a tear resistant material, a

Application No.: 09/974040

Case No.: 56685US002

---

puncture resistant material, a high or low temperature resistant material, high strength, high modulus, adhesive properties, and a flame retardant material.

8. (original) The film of claim 7 wherein the microfiber layer comprises a polypropylene.
9. (original) The film of claim 7 wherein the non-microfiber layer comprises an elastomeric polymer.
10. (previously presented) The film of claim 1 wherein the multi-layer film is selected from the group consisting of a film consisting of two layers and a film consisting of three layers.
11. (original) The film of claim 1 wherein the film comprises a non-microfiber layer comprising a material selected from the group consisting of a polypropylene, a polyethylene, a styrene-ethylene/butylene-styrene block copolymer, a styrene-isoprene-styrene block copolymer, a polyurethane, a fluoropolymer, poly(butylene), poly(isoprene), a nylon, and an adhesive.
12. (original) The film of claim 1 wherein the film comprises two microfiber layers sandwiching a non-microfiber layer.
13. (original) The film of claim 12 wherein the non-microfiber layer is elastomeric.
14. (original) The film of claim 12 wherein the non-microfiber layer comprises a material selected from the group consisting of a polypropylene, a polyethylene, a styrene-ethylene/butylene-styrene block copolymer, a styrene-isoprene-styrene block copolymer, a polyurethane, a fluoropolymer, poly(butylene), poly(isoprene), a nylon, and an adhesive.
15. (original) The film of claim 12 wherein a microfiber layer is a semicrystalline polymer selected from the group consisting of high and low density polyethylene, polypropylene, polyoxymethylene, poly(vinylidene fluoride), poly(methyl pentene), poly(ethylene-chlorotrifluoroethylene), poly(vinyl fluoride), poly(ethylene oxide), poly(ethylene terephthalate),

Application No.: 09/974040

Case No.: 56685US002

---

polyethylene naphthalate , poly(butylene terephthalate), poly(lactic acid), nylon 6 12, nylon 6, nylon 66, polybutene, a thermotropic liquid crystal polymer, a blend of one or more of these polymers, or a copolymer of one or more the named monomers.

16. (canceled)

17. (original) The film of claim 1 wherein the film comprises from about 2 to about 5 layers.

18. (original) The film of claim 1 wherein the film comprises from about 2 to about 5 layers, and the total film thickness prior to fibrillation is in the range from about 25 to about 10,160 microns.

19. (previously presented) The film of claim 1 consisting of two microfiber layers and a non-microfiber layer.

20. (original) The film of claim 1 consisting of 2 microfiber layers.

21. (original) The film of claim 1 consisting of 3 layers: one non-microfiber layer sandwiched by two microfiber layers.

22. (original) The film of claim 1 wherein the microfibers have an average effective diameter of less than 20 microns and a transverse aspect ratio of from 1.5:1 to 20:1.

23. (original) The film of claim 1 wherein the microfibers have an average effective diameter of less than 5 microns.

24. (original) The film of claim 1 wherein the microfibers have an average cross-sectional area of  $0.7 \mu^2$  to  $2.1 \mu^2$ .

25. (canceled)

Application No.: 09/974040

Case No.: 56685US002

---

26. (canceled)

27. (canceled)

28. (canceled)

29. (previously presented) A co-extruded, uni-axially oriented, multi-layer film comprising a non-microfiber layer sandwiched between two microfiber-forming layers, wherein one microfiber layer can be microfibrillated to a hydrophilic surface, and one microfiber layer can be microfibrillated to a hydrophobic surface.

30. (canceled)

31. (canceled)

32. (original) The film of claim 29 consisting of three layers.

33. (canceled)

34. (canceled)

35. (canceled)

36. (original) A multi-layer microfiber article comprising a first microfiber layer at a surface of the article, and second microfiber layer adjacent to the first microfiber-layer, wherein areas of the surface are microfibrillated to form microfibers of only the first layer, and areas of the surface are microfibrillated through the first layer to form microfibers of the second layer.

Application No.: 09/974040

Case No.: 56685US002

---

37. (original) The multi-layer microfiber article of claim 36 wherein a surface of the article includes a pattern comprising a first area of microfibers of one layer of the article, and a second area of microfibers of the second layer.

38. (previously presented) The article of claim 37 wherein an area of microfibers has a property selected from the group consisting of hydrophobicity, hydrophilicity, oleophilicity, and oleophobicity.

39-44. (canceled)

45. (previously presented) A multi-layer film comprising two microfiber layers, wherein one microfiber layer is hydrophilic and one microfiber layer is hydrophobic.

46. (previously presented) The multi-layer film of claim 45 comprising two microfiber layers sandwiching a non-microfiber layer.

47. (previously presented) The film of claim 46 wherein the non-microfiber layer is elastomeric.

48. (previously presented) The film of claim 46 consisting of three layers.

49. (previously presented) The film of claim 46 consisting of three coextruded layers.